



Alloy direct hardening steels

Norma Tuyper BS 970 : 1991



Calidades
Aceros Calibrados

Alloy direct hardening steels



Steel	Chemical Composition							
	C % (m/m)	Si % (m/m)	Mn % (m/m)	P % (m/m)	S % (m/m)	Cr % (m/m)	Mo % (m/m)	Ni % (m/m)
708M40	0,36 to 0,44	0,10 to 0,40	0,70 to 1,00	0,035 max	0,040 max	0,90 to 1,20	0,15 to 0,25	-

