



**Rephosphorized
and Resulfurized Carbon
Steel Bars**

Norma Tuyper ASTM A29/29M



Calidades
Aceros Calibrados



Rephosphorized and Resulfurized Carbon Steel Bars



Grade Designation	Heat Chemical Ranges and Limits %				
	Carbon	Manganese	Phosphorus	Sulfur	Lead
1215	0,09 max	0,75 - 1,05	0,04 - 0,09	0,26 - 0,35	-

Grade Designation	Heat Chemical Ranges and Limits %				
	Carbon	Manganese	Phosphorus	Sulfur	Lead
12L14	0,15 max	0,85 - 1,15	0,04 - 0,09	0,26 - 0,35	0,15 - 0,35

