



Resulfurized Carbon Steel Bars

Norma Tuyper ASTM A29/29M



Calidades
Aceros Calibrados

Resulfurized Carbon Steel Bars

Grade Designation	Heat Chemical Ranges and Limits %			
	Carbon	Manganese	Phosphorus, max	Sulfur, max
1117	0,14 - 0,20	1,00 - 1,30	0,040	0,08 - 0,13

Grade Designation	Heat Chemical Ranges and Limits %			
	Carbon	Manganese	Phosphorus, max	Sulfur, max
1141	0,37 - 0,45	1,35 - 1,65	0,040	0,08 - 0,13

Grade Designation	Heat Chemical Ranges and Limits %			
	Carbon	Manganese	Phosphorus, max	Sulfur, max
1144	0,40 - 0,48	1,35 - 1,65	0,040	0,24 - 0,33

